

锂电池 UN38.3 测试报告 Lithium Battery UN38.3 Test Report

报告编号 Report No.

: AGC09609200503UA03

产 品 名 称 可充电锂离子电池

PRODUCT DESIGNATION Rechargeable Li-ion Battery

商 标 : GivEnergy

样品型号。____

MODEL NAME : Giv-BAT8.2

委 托 单 位 : JMHING POWER LTD

签 发 日 期 : 2020-06-30

DATE OF ISSUE

检测标准。《联合国关于危险品运输建议书—试验和标准手册》

STANDARD(S) : (ST/SG/AC.10/11/Rev.6/Amend.1)

报告版本

REPORT VERSION : V1.0

深圳市鑫宇环检测有限公司

Attestation of Global Compliance (Shenzhen) Co., Ltd.

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the specificated restrict inspection. Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written definition of AGE. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15day after the issued of the test report Further enquiry of validity or verification of the test report should be addressed to AGC by agc@agc-cert.com.



1. 样品描述 Sample	Description		
样品名称 Sample Name	可充电锂离子电池 Rechargeable Li-ion Battery	样品型号 Model Name	Giv-BAT8.2
测试实验室 Testing laboratory	深圳市鑫宇环检测有限公司 Attestation of Global Complianc	e (Shenzhen) Co., Ltd.	5 5 50
测试地址 Testing Address	深圳市宝安区福海街道和平社区 1, 2/F, Building 19, Junfeng Indu Street, Bao'an District, Shenzhe	ustrial Park, Chongqing Road	
委托单位 Applicant	JMHING POWER LTD	, NO 100	, c
委托单位地址 Applicant Address	UNIT 5 TOWER HOUSE LANE ROAD, HULL, HU12 8EE, UK	INDUSTRIAL ESTATE, TOV	VER HOUSE LANE, HEDON
生产单位 Manufacturer	深圳市给力能源科技有限公司 Shenzhen GivEnergy Technolog	gy Co Ltd	CO 2
生产单位地址 Manufacturer Address	深圳市宝安区象山大道 225 号 4 4th Floor 225th Building Xiang S		Guang Dong China
电芯生产单位 Manufacturer Of Cell	江西星盈科技公司有限公司 JiangXi Star Energy Technology	/ Co., Ltd	30 CC CC
用途 Use	储能户用 Energy storage household use	30 20	
电池类型 Battery Type	可充电锂电池组 Rechargeable Li Battery	组成方式 Composing Mode	16S1P
标称电压 Nominal Voltage	51.2V	额定容量 Rated Capacity	160Ah
瓦时 Watt-hour	8192Wh	形状 Form	近长方体 Almost Cuboid
充电上限电压 Limited Charge Voltage	57.2V	截止电压 Cut-off Voltage	46.4V
充电电流 Charge Current	60A	最大持续充电电流 Max. Continuous Charge Current	60A
最大持续放电电流 Max. Continuous Discharge Current	80A	充电截止电流 End Charge Current	8A
电芯型号 Cell Model	SLA45173184-160Ah	电芯容量 Cell Rated Capacity	160Ah
开始时间 Client Date	2020-06-10	完成时间 Completing Date	2020-06-30



2、测试标准 Standard

《联合国关于危险品运输建议书—试验和标准手册》(ST/SG/AC.10/11/Rev.6/Amend.1)

<United Nations Recommendations on the Transport of Dangerous Goods: Manual of Tests and Criteria> (Sixth revised edition Amend 1)

3、测试项目及结论 Test Item And Conclusion

测试项目 Item	测试样品编号 Samples Number	结论 Conclusion
高度模拟 Altitude simulation		
温度试验 Thermal test	振动 Vibration Z1~Z2 X1~X2 冲击 Shock	通过 Pass
振动 Vibration		通过 Pass
冲击 Shock		通过 Pass
外部短路 External Short Circuit		通过 Pass
挤压 Crush	Z3~Z7 X3~X7	通过 Pass
过度充电Overcharge	Z8~Z9 X8~X9	通过 Pass
强制放电 Forced discharge	Z10~Z19 X10~X19	通过 Pass

送检样品符合《联合国关于危险品运输建议书—试验和标准手册》(ST/SG/AC.10/11/Rev.6/Amend.1), 38.3 章 的要求。

The submitted samples were complied with <United Nations Recommendations on the Transport of Dangerous Goods: Manual of Tests and Criteria>(Sixth revised edition Amend 1), sub-section 38.3.

报告修订记录 R	eport Revise	Record:
----------	--------------	---------

				(8)
版本号	修改次数	签发日期	有效性	备注
Report Version	Revise Time	Issued Date	Valid Version	Notes
V1.0	1	Jun. 30, 2020	有效	首次发行
V 1.0	,	Juli. 30, 2020	Valid	Initial release

C	主检人 Tested by	王	AR	审核人 Reviewed by	薛连连	批准人 Approved by	放为体	
---	------------------	---	----	--------------------	-----	--------------------	-----	--

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the Bedicated Restroy/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15day after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc@agc~cert.com.



样品描述及说明 Description of the sample

Z1~Z2, 第1个交替充电放电周期完全充电状态的电池;

Z3~Z7 Batteries at first cycle in fully charged states;

X1~X2, 第25个交替充电放电周期结束后完全充电状态的电池;

X3~X7

Batteries after 25 cycles ending in fully charged states;

Z8~Z9 第1个交替充电放电周期完全充电状态电芯容量设计值50%的电芯:

Cells at first cycle at 50% of the design rated capacity;

X8~X9 第25个交替充电放电周期完全充电状态电芯容量设计值50%的电芯;

The 25th cycle of charging and discharging 50% of the battery cell in rated

capacity state;

Z10~Z19 第一个充放电周期完全放电状态的电芯;

Cells at first cycle in fully discharged states;

X10~X19 第25个交替充电放电周期结束后完全放电状态的电电芯;

Cells after 25 cycles ending in fully discharge states.

可能的试验情况判定 Test case verdicts:

一要求不适用本产品 Test case does not apply to the test object N/A(Not applicable)

一试验结果符合要求 Test item does meet the requirement P(ass)

一试验结果不符合要求 Test item does not meet the requirement F(ail)


Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the bedicated resting/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC he test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15day after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc@agc-cert.com.



4、样品图片 Sample Photos


Product Name: Rechargeable Li-ion Battery
Model Type: Giv-Bat8.2
Nominal Voltage: 51.2Vd.c.
Rated Capacity: 160Ah
Nominal Capacity(25°C): 8192Wh






Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the Bedicated Residual Residual







仅对原报告照片中的样品负责 Authenticate the photo on original report only



5、测试方法及判定 Test Method And Verdict

章节 Clause	标准要求 Requirements	测试结果 Result	判定 Verdict
38.3.4.1	测试 1: 高度模拟 Test 1: Altitude simulation	见表 1 See Table 1	Р
, C	试验电池和电池组应压力不大于11.6kpa和环境温度为20±5℃的条件下贮存不少于6个小时。 Test cells and batteries shall be stored at a pressure of 11.6kPa or less for at least six hour at ambient temperature (20±5℃)	无渗漏,无排 气,无解体,无 破裂和无起火。 No leakage, no venting, no	P
	要求电池和电池组无渗漏、无排气、无解体、无破裂和无起火,并且每个试验电池或电池组在试验后的开路电压不小于其在进行这一试验前电压的90%。有关电压的要求不适用于完全放电状态的试验电池和电池组。	disassemble, no rupture and no fire.	30
OC.	Cells and batteries meet this requirement if there is no leakage, no venting, no disassemble, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.		
38.3.4.2	测试 2:温度试验 Test 2: Thermal test	见表 2 See Table 2	Р
	试验电池和电池组先在试验温度等于72℃±2℃的条件下存放至少6小时,接着再在试验温度等于-40℃±2℃的条件下存放至少6小时。两个极端试验温度之间的最大时间间隔为30分钟。此程序重复进行,共完成10次,接着将所有试验电池和电池组在环境温度(20℃±5℃)下存放24小时。对于大型电池和电池组,暴露于极端试验温度的时间至少应为12小时。 Test cells and batteries are to be stored for at least six hours at a test temperature equal to 72±2℃, followed by storage for at least six hours at a test temperature equal to −40±2℃. The maximum time interval between test temperature extremes is 30 minutes. This procedure is to be repeated until 10 total cycles are complete, after which all test cells and batteries are to be stored for 24 hours at ambient temperature (20 ± 5℃). For large cells and batteries the duration of exposure to the test temperature extremes should be at least 12 hours.	See Table 2 无渗漏,无排气,无解体,无破裂和无起火。 No leakage, no venting, no disassemble, no rupture and no fire.	P
	要求电池和电池组无渗漏、无排气、无解体、无破裂和无起火,并且每个试验电池或电池组在试验后的开路电压不小于其在进行这一试验前电压的90%。有关电压的要求不适用于完全放电状态的试验电池和电池组。 Cells and batteries meet this requirement if there is no leakage, no venting, no disassemble, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.		

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the Bedicated Festing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the writter exhorization of AGC, whe test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15day after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc@agc-cert.com.



章节 Clause	标准要求 Requirements	测试结果 Result	判定 Verdict
38.3.4.3	测试3: 振动 Test 3: Vibration	见表 3 See Table 3	Р
	电池和电池组紧固于振动机平台,但不得造成电池变形,并能准确可靠地传播振动。振动应是正弦波形,对数扫描频率在 7 赫兹和 200 赫兹之间,再回到 7 赫兹,跨度为 15 分钟。这一振动过程须对三个互相垂直的电池安装方位的每一方向重复进行 12 次,总共为时 3 小时。其中一个振动方向必须与端面垂直。 Cells and batteries are firmly secured to the platform of the vibration machine without distorting the cells in such a manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal waveform with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting positions of the cell. One of the directions of vibration must be perpendicular to the terminal face. 作对数式频率扫描,对总质量不足 12 千克的电池和电池组(电池和小型电池组),和对 12 千克及更大的电池组(大型电池组)有所	无渗漏,无排气,无解体,无破裂和无起火。 No leakage, no venting, no disassemble, no rupture and no fire.	P C
	不同。 The logarithmic frequency sweep shall differ for cells and batteries with a gross mass of not more than 12 kg (cells and small batteries), and for batteries with a gross mass of more than 12 kg	NGC .	P.G.C.
	(large batteries). 对电池和小型电池组:从7赫兹开始,保持1gn的最大加速度,直到频率达到18赫兹。然后将振幅保持在0.8毫米(总偏移1.6毫米),并增加频率直到最大加速度达到8gn(频率约为50赫兹)。将最大加速度保持在8gn直到频率增加到200赫兹。		gC .
	For cells and small batteries: from 7 Hz a peak acceleration of $1g_n$ is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of $8g_n$ occurs (approximately 50 Hz). A peak acceleration of $8g_n$ is then maintained until the frequency is increased to 200 Hz.		>S
	对大型电池组:从7赫兹开始,保持1gn的最大加速度,直到频率达到18赫兹。然后将振幅保持在0.8毫米(总偏移1.6毫米),并增加频率直到最大加速度达到2gn(频率约为25赫兹)。将最大加速度保持在2gn直到频率增加到200赫兹。	CC.	
	For large batteries: from 7 Hz to a peak acceleration of $1g_n$ is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of $2g_n$ occurs (approximately 25 Hz). A peak acceleration of $2g_n$ is then maintained until the frequency is increased to 200 Hz.	CC FC	
F.G.C	要求电池和电池组试验中和试验后无渗漏、无排气、无解体、无破裂和无起火,并且每个试验电池或电池组在第三个垂直安装方位上的试验后立即测得的开路电压不小于在进行这一试验前电压的	C	



章节 Clause		标准要求 Requirements		测试结果 Result	判定 Verdict
NGC C	Cells and b no venting, no c circuit voltage o than 90% of its requirement rela	的要求不适用于完全放电状态的记 atteries meet this requirement if the disassemble, no rupture and no fir f each test cell or battery after test voltage immediately prior to this parting to voltage is not applicable to discharged states.	here is no leakage, e and if the open ting is not less procedure. The	C NCC	
38.3.4.4	测试4:冲击 Test 4: Shock		100	见表 4 See Table 4	Р
	个试验电池组的 Test cells ar by means of a r of each test batt 每个电池需约 波冲击。针对大 的半正弦波冲击 Each cell sh acceleration of Alternatively, lar peak acceleration 每个电池组成 击。对于小型电 冲持续时间应为 度。	nd batteries shall be secured to the igid mount which will support all natery. 圣受最大加速度150gn和脉冲持续时型电池需经受最大加速度50gn和脉冲持续时间。 all be subjected to a half-sine shound shall be subjected to a half-sine shound for any be subjected to a half or of 50gn and pulse duration of 1 位根据电池组的质量而受到峰值加速过程的脉冲持续时间应6毫秒,对于11毫秒,下面的公式用于计算适当	e testing machine nounting surfaces I 间6毫秒的半正弦 A 冲持续时间11毫秒 ck of peak iseconds. alf-sine shock of 1 milliseconds. is 應度的半正弦波冲于大型电池组的脉 i 的最小峰值加速	无渗漏,无排气,无解体,无破裂和无起火。 No leakage, no venting, no disassemble, no rupture and no fire.	P
	电池 Battery	最小峰值加速度 Minimum peak acceleration	脉冲持续时间 Pulse duration	100	5
,c	小型电池 Small batteries	150g _n 或公式结果中的较小值 150g _n or result of formula Acceleration $(g_n) = \sqrt{\frac{100850}{mass^*}}$ whichever is smaller	6毫秒 6ms		Fac.
	大型电池 Large batteries	$50g_n$ 或公式结果中的较小值 $50g_n$ or result of formula $Acceleration (g_n) = \sqrt{\frac{3000}{mass}^*}$ whichever is smaller	11毫秒 11ms	NGC N	gC .
	* 质量	生单位用千克计算 Mass is expressed in I	kilograms.	10	
NGC.	acceleration del	r shall be subjected to a half-sine pending on the mass of the batter e 6 milliseconds for small batteries large batteries. The formulas belo	y. The pulse s and 11	C CC	35



章节 Clause	标准要求 Requirements	测试结果 Result	判定 Verdict
	calculate the appropriate minimum peak accelerations. 每个电池或电池组需在三个互相垂直的安装方位的正方向经受三次冲击,接着在反方向经受三次冲击,总共经受18次冲击。 Each cell or battery is subjected to three shocks in the positive direction followed by three shocks in the negative direction of each of three mutually perpendicular mounting positions of the cell for a total of 18 shocks. 要求电池和电池组无渗漏、无排气、无解体、无破裂和无起火,并且每个试验电池或电池组在试验后的开路电压不小于其在进行这一试验前电压的90%。有关电压的要求不适用于完全放电状态的试验电池和电池组。 Cells and batteries meet this requirement if there is no leakage, no venting, no disassemble, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.		
38.3.4.5	测试 5: 外部短路 Test 5: External Short Circuit	见表 5 See Table 5	Р
) L	待测试的电池或电池组应加热一段时间,以使其外表面温度达到 均匀稳定的 57±4℃的温度。加热时间取决于电池或电池组的大小和设计,并应进行评估和记录。如果这种评估是不可行的,对于小型电池和小型电池组至少在 57±4℃的环境下存放 6 小时,对于大型电池和大型电池组至少在 57±4℃的环境下存放 12 小时。然后电池或电池组在 57±4℃的环境中,应接受一个外部总阻值小于 0.1 欧姆的短路条件。	无解体,无破裂,无起火。 No disassemble, no rupture and no fire.	P
	The cell or battery to be tested shall be shall be heated for a period of time necessary to reach a homogeneous stabilized temperature of 57±4°C, measured on the external case. This period of time depends on the size and design of the cell or battery and should be assessed and documented. If this assessment is not feasible, the exposure time shall be at least 6 hours for small cells and small batteries, and 12 hours for large cells and large batteries. Then the cell or battery at 57±4°C shall be subjected to one short		NO.
	circuit condition with a total external resistance of less than 0.1 ohm. 这一短路条件应在电池或电池组的外壳温度回到 57±4℃后继续短路 1 小时,或对于大型电池组其外壳温度已下降了一半的最大升温,	P.G.C	gC
	并保持低于该值。短路和冷却过程至少在环境温度中进行。 This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to 57 ± 4 °C, or in the case of the large batteries, has decreased by half of the maximum temperature increase observed during the test and remains below that value. The short circuit and cooling down phases shall be conducted at least at ambient temperature.	ranjis.	Š N

Attestation of Global Compliance(Shenzhen)Co., Ltd

Tel: +86-755 2523 4088 E-mail: agc@agc-cert.com Web: http://cn.agc-cert.com/



章节 Clause	标准要求 Requirements	测试结果 Result	判定 Verdict
GC	要求电池和电池组外壳温度不超过 170℃,并且在试验过程中及 试验后 6 小时内无解体,无破裂,无起火。 Cells and batteries meet this requirement if their external temperature does not exceed 170℃ and there is no disassemble, no rupture and no fire within six hours of this test.	C CC)
38.3.4.6	测试 6: 撞击/挤压 Test 6: Impact / Crush	见表 6 See Table 6	Р
	撞击 (适用于直径大于等于 18 毫米的圆柱形电池) Impact (applicable to cylindrical cells not less than 18mm in diameter)	N/A	N/A
GC,	and no fire during the test and within six hours after this test. 挤压(适用于棱柱形、袋装、硬币/纽扣电池和直径小于 18 毫米的圆柱形电池) Crush (applicable to prismatic, pouch, coin/button cells and cylindrical cells less than 18mm in diameter) 将电池或元件电池放在两个平面之间挤压,挤压力度逐渐加大,	无解体,无破裂,无起火。 No disassemble, no rupture and no fire	P

/Inspection The test results



章节 Clause	标准要求 Requirements	测试结果 Result	判定 Verdict
	在第一个接触点上的速度大约为1.5厘米/秒。挤压持续进行,直到出		J
	现以下三种情况之一:		- C
	(a) 施加的力量达到13千牛±0.78千牛;	0	
	(b) 电池的电压下降至少100毫伏;或		(6)
	(c) 电池变形达原始厚度的50%或以上。		- C
	A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached. (a) The applied force reaches 13kN±0.78kN;	NGC .	-3C
	(b) The voltage of the cell drops by at least 100mV; or		
	(c) The cell is deformed by 50% or more of its original thickness. 一旦达到最大压力、电压下降 100 毫伏或更多,或电池变形至少达原厚度的 50%,即可解除压力。	CC C	
	Once the maximum pressure has been obtained, the voltage drops by 100mV or more, or the cell is deformed by at least 50% of its original thickness, the pressure shall be released.	C C	
	楼柱形或袋装电池应从最宽的一面施压。纽扣/硬币形电池应从其 平坦表面施压。圆柱形电池应从与纵轴垂直的方向施压。		GC
	A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis. 每个试样电池或元件电池只做一次挤压试验。试样应继续观察 6 小时。试验应使用之前未做过其他试验的电池或元件电池进行。	FCC F	gC .
	Each test cell or component cell is to be subjected to one crush only. The test Samples shall be observed for a further 6 h. The test shall be conducted using test cells or component cells that have not previously been subjected to other tests. 要求电池和电池组外壳温度不超过170℃,并且在试验过程中及	C NO	Š M
	试验后6小时内无解体,无起火。		
,0	Cells and component cells meet this requirement if their external temperature does not exceed 170°C and there is no disassemble and no fire during the test and within six hours after this test.	0	P.O.
38.3.4.7	测试 7: 过充电	见表 7	Р
30.3.4.7	Test 7: Overcharge	See Table 7	
P.C.	充电电流必须是制造商建议的最大持续充电电流的两倍。试验的最小电压如下: (a)制造商建议的充电电压不大于18伏时,试验的最小电压应是电池组最大充电电压的两倍或22伏两者中的较小者; (b)制造商建议的充电电压大于18伏时,试验的最小电压应为最大充电电压的1.2倍。	无分解,无 起火。No disassemble and no fire.	Р

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the specificated feet Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15day after the issue of Further enquiry of validity or verification of the test report should be addressed to AGC by agc@agc-cert.com.



章节 Clause	标准要求 Requirements	测试结果 Result	判定 Verdict
GC A	The charge current shall be twice the manufacturer's recommended maximum continuous charge current. The minimum voltage of the test shall be as follows: (a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. (b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. Tests are to be conducted at ambient temperature; the duration of the test shall be 24 hours.		
	要求充电电池组在试验过程中和试验后 7 天内无解体,无起火。 Rechargeable batteries meet this requirement if there is no disassemble and no fire during the test and within seven days after the test.	GC NO	
88.3.4.8	测试 8: 强制放电 Test 8: Forced discharge	见表 8 See Table 8	Р
	每个电池应在环境温度下与 12V 直流电源上进行强制放电,此直流电源串联在起始电流等于制造商给定的最大放电电流条件下强制放电。 Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12V D.C. power supply at an initial current equal to the maximum discharge current specified by the manufacturer. 将适当大小和额定值的电阻负荷与试验电池串联,计算得出给定的放电电流。对每个电池进行强制放电,放电时间(小时)应等于其额定容量除以初始试验电流(安培)。 The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell shall be forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere).	无分解,无起火。 No disassemble and no fire.	P
	要求原电池或充电电池在试验过程中和试验后 7 天内无解体,无起火。 Primary or rechargeable cells meet this requirement if there is no disassemble and no fire during the test and within seven days after the test.	No.	GC



6、测试数据 Test Data

表 1 Table 1	高度模拟 Altitude simulation						Р	
样品	质量 M	质量 Mass (kg)		电压 Voltage (V)			有无渗漏,排气,	
编号 Sample No.	测试前 Pre-test	测试后 After test	质量亏损 Mass loss (%)	测试前 Pre-test	测试后 After test	电压亏损 Voltage loss (%)	解体,破裂和起火 Whether leakage, venting, disassemble, rupture, fire (Y/N)	
Z1	72.36	72.36	0.000	56.10	56.09	0.02	N	
Z2	72.28	72.28	0.000	56.08	56.08	0.00	N	
X1	72.31	72.31	0.000	56.09	56.09	0.00	N	
X2	72.32	72.32	0.000	56.10	56.10	0.00	N	

表 2 Table 2	温度试验 Thermal test						Р
17X 12	质量 M	lass (kg)	电压 Voltage (V)		有无渗漏,排气,		
样品 编号 Sample No.	测试前 Pre-test	测试后 After test	质量亏损 Mass loss (%)	测试前 Pre-test	测试后 After test	电压亏损 Voltage loss (%)	解体,破裂和起火 Whether leakage, venting, disassemble, rupture, fire (Y/N)
Z 1	72.36	72.35	0.000	56.09	55.83	0.46	N
Z2	72.28	72.28	0.000	56.08	55.84	0.43	o N
X1	72.31	72.31	0.000	56.09	55.83	0.46	N
X2	72.32	72.32	0.000	56.10	55.84	0.46	N

表 3 Table 3	振动 Vibration						Р
	质量 M	ass (kg)		电压 Voltage (V)			有无渗漏,排气,
样品编号 Sample No.	测试前 Pre-test	测试后 After test	质量亏损 Mass loss (%)	测试前 Pre-test	测试后 After test	电压亏损 Voltage loss (%)	解体,破裂和起火 Whether leakage, venting, disassemble, rupture, fire (Y/N)
Z1	72.35	72.35	0.000	55.83	55.83	0.00	N
Z2	72.28	72.28	0.000	55.84	55.83	0.02	N
X1	72.31	72.31	0.000	55.83	55.83	0.00	N
X2	72.32	72.32	0.000	55.84	55.84	0.00	N

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the Bedicated Pesting/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the writter authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15day after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc@agc-cert.com.



表 4 Table 4		6	Р				
	质量 Mass (kg)		电压 Voltage (V)			有无渗漏,排气,解	
样品编号 Sample No.	测试前 Pre-test	测试后 After test	质量亏 损 Mass loss (%)	测试前 Pre-test	测试后 After test	电压亏损 Voltage loss (%)	体,破裂和起火 Whether leakage, venting, disassemble, rupture, fire (Y/N)
Z1	72.35	72.35	0.000	55.83	55.82	0.02	N
Z2	72.28	72.28	0.000	55.83	55.83	0.00	N
X1	72.31	72.31	0.000	55.83	55.83	0.00	N O
X2	72.32	72.32	0.000	55.84	55.84	0.00	N

表 5 Table 5	外短路 External short circuit	PO		
样品编号 Sample No.	最高温度 Peak temperature (°C)	有无解体,破裂,起火 Whether disassemble, rupture, fire (Y/N)		
Z1	58.4	N		
Z2	58.6	N		
X1 58.1		ON CN		
X2 58.8		N		


表 6 Table 6 挤压 Crush		P P			
样品编号 Sample No.	最高温度 Peak temperature (°C)	有无解体,起火 Whether disassemble, fire (Y/N)			
Z3	23.4	O N			
Z4	23.1	N			
Z5	23.2	N			
Z6	23.5	N ®			
Z7	23.1	N			
Х3	23.2	N			
X4	23.0	G N			
X5	23.2	N			
X6	22.9	N			
X7	G N				



表 7 Table 7	过度充电 Overcharge	100	Р	,0	
样品编号 Sample No.	W	有无解体,起火 hether disassemble, f			
Z8		N	110 (1714)		3
Z9	30 -0	N		10	
X8		N	(8)		
X9	0	N	-C	@	

表 8 Table 8	强制放电 Forced discharge	Р	100			
样品编号	有无解体,起火					
Sample No.	Whether disassemble, fire (Y/N)					
Z10	-C	0				
Z11		0				
Z12	0	N	8			
Z13		N				
Z14	NO GC	N	P. 10			
Z15	0	N	8			
Z16	-6	N	-00			
Z17	10	N				
Z18		N	2.G			
Z19	· ·	2.C °				
X10	-C	N	0			
X11		N				
X12	0	N	8			
X13	30 - 6	N	20			
X14		N				
X15	®	N	0			
X16		N	- CO -			
X17	10° 20	N	Par 100			
X18	N					
X19	N N					







8、测试设备 Test equipment

电子台秤 Electronic Scale
数字万用表 Digital multimeter
高性能电池测试系统 Battery Testing System
真空试验箱 Vacuum Tester
快速温变试验箱 Rapid Temperature Change Tester
振动试验台 Vibration test instrument
冲击试验台 Mechanical shock test instrument
温控型电池短路试验机 Battery Short-circuit Tester
电池挤压试验机 Battery Crush Tester
数据采集仪 Data Acquisition Instrument
TPR 系列高精度直流稳压电源 DC power supply
动力电池检测系统 Power Battery Detection System

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the Bedicated Festing/Inspection Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC within 15day after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc@agc-cert.com.



声明

Statement

1.本报告无本公司报告专用章和批准人签章无效。

This report is invalid without the special seal for report of AGC and the signatures of approver.

2.本报告涂改和删除无效。

This report is invalid if it is blotted out and deleted.

- 3.委托单位对检测结果有异议,应于收到报告之日起 15 日内向我司提出。 If the applicant has any questions about results, shall submit to AGC within 15 days.
- 4.本报告仅对客户所送样品负责。

This report is responsible for the sample provided by the client only.

5.未经本公司许可,不得部分复制、摘用本报告内容。

This report shall not be reproduced except in full, or extracted without the written approval of AGC.

6.本报告复印件未加盖红章无效。

This report photocopy is invalid without the red chop.

----报告结束---***End of report***

Any report having not been signed by authorized approver, or having been altered without authorization, or having not been stamped by the condicated restrouting portion of Stamp" is deemed to be invalid. Copying or excerpting portion of, or altering the content of the report is not permitted without the written authorization of AGC. The test results presented in the report apply only to the tested sample. Any objections to report issued by AGC should be submitted to AGC within 15days after the issuance of the test report. Further enquiry of validity or verification of the test report should be addressed to AGC by agc@agc~cert.com.